

OSMO product recommendations for different wood varieties

Timber Type	Polyx Oil	Woodwax Clear Extra Thin	Woodwax Colour Transparent
Acacia	Yes	No	Possible
Ash	Yes	No	Yes
Baltic Pine	Yes	No	Yes
Bamboo	Yes	No	Possible
Beech	Yes	No	Yes
Birch	Yes	No	Yes
Blackbutt	Yes	No	Yes
Brushbox	Yes	No	Possible
Cherry	Yes	No	Possible
Cork	Yes	No	Yes
Douglas Fir (Oregon)	Yes	No	Yes
Elm	Yes	No	Yes
Eucalyptus - Dry (Saligna, Vic. Ash, Red and Blue Gum	Yes	No	Yes
Eucalyptus – Oily (Spotted Gum, Tallow Wood)	Possible	Yes	Possible
IPE	No	Yes	No
Iroko	No	Yes	No
Jarrah	Yes	No	No
Jatoba	No	Yes	No
Kwila/Merbau/Batu	Possible	Yes	No
Larch	Yes	No	Yes
Mahogany	No	Yes	No
Maple	Yes	No	Yes
MDF/Particle Board (new)	Yes	No	Yes
Oak	Yes	No	Yes
Pine	Yes	No	Yes
Poplar	Yes	No	Yes
Rosewood	No	Yes	No
Spruce/Fir/Cypress	Yes	No	Yes
Tasmanian Oak	Yes	No	Yes
Teak	Yes	No	Possible
Walnut	Yes	No	Possible
Wenge	No	Yes	No

Where “Possible” has been indicated, a test should be done to establish suitability, and drying time. If the oil does not dry as it should, then it is **not suitable**, and an alternative OSMO product should be considered.